

Ultra-High Sheen 7000

- Weight per gallon = 7.55 pounds per gallon
- Weight solids = 25.75%
- Volume solids = 21.23%
- Coverage = approx. 340.53 square feet per gallon at 1 mil film thickness. It is depended on porosity and surface roughness of cement.
- VOC content = < 100 grams per liter Moisture Loss (ASTM C156) < 0.40 grams per meter²
- Drying time = < 1 hour Recoat = 2 hours
- Foot traffic = 24 hours
- Vehicle traffic = 72 hours
- Adhesion to concrete is excellent
- Alkali resistance (after 48 hour cure) is excellent
- Gasoline resistance = slight dulling
- Solvent resistance is minimal
- UV exposure is excellent
- Minimum working temperature is 50 degree F.