

Ultra-Medium Sheen 1000

- Weight per gallon = 8.53 pounds per gallon
- Weight solids = 25.90%
- Volume solids = 23.93%
- Coverage = approx. 383 square feet per gallon at 1 mil film thickness. It is depended on porosity and surface roughness of cement.
- VOC content = 51.11 grams per liter
- Drying time = 2 to 3 hours at 70 degrees F and 50% relative humidity
- Recoat = 4 hours
- Foot traffic = 24 hours
- Vehicle traffic = 48 hours
- Adhesion to concrete is excellent
- Block resistance is excellent
- Abrasion resistance is excellent
- Blush resistance is excellent
- Hot tire pick up resistance is excellent
- Alkali (dilute) resistance (after 48 hour cure) is excellent
- Brake fluid resistance is excellent
- Transmission fluid resistance is excellent
- Solvent resistance is minimal
- UV exposure is excellent
- Minimum working temperature is 55 degree F.