

SEALER DEPOT ULTRA-SHEEN 3000

CLEAR ACRYLIC SOVENT BASE MATTE GLOSS CONCRETE SEALER

1 DESCRIPTION

This is a matte gloss pure acrylic cure and seal that protects concrete surfaces such as stamped concrete. This sealer has a flat finish that is non- yellowing. Because of its flat finish it will not enhance the color of stamped concrete or integral color concrete as that of a high gloss sealer. This sealer will provide protection against the damaging effects of UV light, weather, traffic, salt spray, dilute acids and alkali. It is highly recommended for exterior use.

2 USES

Stamped concrete
Integral colored concrete
Terrazzo
Acid stain concrete
Concrete pavers
Concrete swimming pool deck

3 TECHNICAL INFORMATION

Weight per gallon = 7.89 pounds per gallon
Weight solids = 31.50%
Volume solids = 24.87%
Coverage = approx. 398.91 square feet per gallon at 1 mil film thickness. It is depended on porosity and surface roughness of cement.
VOC content = < 700 grams per liter
Moisture Loss (ASTM C156) < 0.40 grams per meter²
Drying time = < 1 hour
Recoat = 2 hours
Foot traffic = 24 hours
Vehicle traffic = 72 hours
Adhesion to concrete is excellent
Alkali resistance (after 48 hour cure) is excellent
Gasoline resistance = slight dulling
Solvent resistance is minimal

UV exposure is excellent
Minimum working temperature is 50 degree F.

4 APPLICATION

SURFACE PREPARATION

The concrete surface must be clean of all oils, wax, grease and standing water. This sealer cannot be applied over an existing water base sealer. If the concrete is already sealed with any sealer, the old sealer should be completely stripped away and the surface cleaned and dried.

ROLLER APPLICATION

Apply sealer with a roller and pan. Do not pour this sealer directly on the concrete surface. Roll in one direction and then back roll. A 3/8 inch nap solvent resistant cover is recommended. Do not apply at temperatures below 50 degrees F and above 80 degrees F. A second coat is recommended.

SPRAY APPLICATION

Apply sealer with a hand held industrial pump or airless sprayer. If conditions are extremely hot or windy adjust the spraying technique to prevent dry spraying.

For best results, the matte finish sealer should be the second coat over the first coat of high gloss sealer. Apply the matte sealer after 2 to 3 hours of applying the first coat high gloss sealer. Always test a small area of the concrete surface to verify protection and appearance. Always apply this sealer in good ventilated areas. Always apply sealer in thin even coats to prevent bubbling and cracking. Never apply this sealer on foggy and rainy days. Use Stampcrete cleaning solvent for cleanup of equipment immediately after use.

5 MAINTENANCE

Inspect the sealer surface regularly for signs of dirt and wear. Clean the surface as needed with detergent and water. Rinse with water after cleaning. If surface appears dull from excessive wear over time, apply an additional coat of sealer to restore original luster of the surface.

6 SAFETY

Always store in a ventilated area. Keep the sealer away from heat, sparks and open flame. Keep the sealer out of reach of children. Do not breathe in vapors or mist. A respirator mask or approved organic vapor mask is recommended when applying the sealer. Avoid contact with skin or eyes. In case of contact, flood affected area with water. If irritation persists, see a physician. Always close the container tightly when not in use.

7 PACKAGING

1 gallon cans: 8.03 pound

5 gallon pails: 40.15 pounds

55 gallon drums: 441.65 pounds

8 SHELF LIFE

2 years in open container
